



Guide Specification

PART 1 GENERAL

1.1 SUMMARY

- A. Provide labor, materials, equipment and supervision necessary to install a general use epoxy flooring system as outlined in this specification.
- B. The manufacturers application instructions for each product used are considered part of this specification and should be followed at all times.
- C. Related Sections:
 1. Section 03 30 00 - Cast-in-Place Concrete
 2. Section 07 92 00 - Joint Sealants
 3. Section 07 95 00 - Expansion Control

1.2 SYSTEM DESCRIPTION

- A. WG-32 shall be a complete system of compatible materials supplied by NEOGARD® to create a general use epoxy flooring system.
- B. WG-32 shall be designated for application on the specific type of substrate indicated on the drawings.

1.3 SUBMITTALS

- A. Product Data: Submit NEOGARD® product literature and installation instructions.
- B. Project Reference List: Submit list of projects as required by this specification.
- C. Samples: Submit samples of specified high performance epoxy flooring system. Samples shall be construed as examples of finish only.
- D. Applicator Approval: Submit letter from manufacturer stating applicator is approved to install the general use epoxy flooring system.
- E. Warranty: Submit copy of manufacturers standard warranty.

1.4 QUALITY ASSURANCE

- A. Supplier Qualifications: WG-32, as supplied by NEOGARD®, is approved for use on this project.

- B. Applicator Qualifications: Applicators shall be approved to install specified system.

1.5 DELIVERY, STORAGE AND HANDLING

- A. Delivery: Materials shall be delivered in original sealed containers, clearly marked with supplier's name, brand name and type of material.
- B. Storage and Handling: Recommended material storage temperature is 75°F (23.8°C). Handle products to avoid damage to container. Do not store for long periods in direct sunlight.

1.6 PROJECT CONDITIONS

- A. Environmental Conditions:
 1. Do not proceed with application of materials when substrate temperature is less than 50°F (10°C). It is recommended to maintain a minimum concrete temperature of 50°F (10°C) for a minimum of 48 hours before, during and after installation, or until cured.
 2. Concrete must be free of hydrostatic, capillary or moisture vapor pressure. Substrates in contact with ground must have a properly installed, effective vapor barrier to help prevent potential problems resulting from hydrostatic, capillary or moisture vapor pressure. Moisture content of concrete not to exceed four pounds per 1,000 square feet per 24 hours when tested by the referee or quantitative calcium chloride test method.
 3. Do not apply materials unless surface to receive coating is clean and dry.

1.7 WARRANTY

- A. Upon request, NEOGARD® shall offer the manufacturer's standard warranty upon receipt of a properly executed warranty request form.

PART 2 PRODUCTS

2.1 MANUFACTURER

- A. NEOGARD® Division of JONES-BLAIR® Company, P.O. Box 35286, Dallas, TX 75235, Toll Free (800) 321-6588, Fax (214) 357-7532, www.neogard.com.

2.2 MATERIALS

- A. WG-32:
 1. Crack and Joint Filler: 70718/70719 flexible epoxy.
 2. Fillers: P1934 fumed silica and 86364 blended aggregates.

3. Epoxy: 70714/70715-09 clear or pigmented.
4. Sealant: 70991 or other polyurethane sealant approved by NEOGARD®.
5. Texture: 86500 Neogrip spheres.

2.3 MATERIAL PERFORMANCE CRITERIA

- A. Typical performance requirements of cured 70714/70715-09 epoxy used on this project are:

PERFORMANCE REQUIREMENTS OF CURED FILM		
PHYSICAL PROPERTIES	TEST METHOD	RESULTS
Compressive Strength	ASTM D695	15,000 psi
Tensile Strength	ASTM D638	2,000 psi
Elongation	ASTM D638	40%
Flexural Strength	ASTM D790	1,900 psi
Flexural Modulus	ASTM D790	62,000 psi
Shore D Hardness	ASTM D2240	77
Adhesion	ASTM D4541	400 psi
Taber Abrasion (cs17)	ASTM D4060	61 mg/1,000 rev
Water Resistance	ASTM D570	0.17%
MVT @ 10 mils	ASTM E96	0.18 Perm
Impact Flexibility	ASTM D6905-03	Pass @ 120 in/lb

2.4 MIXES

- A. Comply with manufacturer's instructions for mixing procedures.
- B. Carefully measure and mix the components together.

PART 3 EXECUTION

3.1 EXAMINATION

- A. Verify that the work done under other sections meets the following requirements:
 1. That the concrete substrate surface is free of ridges and sharp projections, sound and dry.
 2. That the concrete was cured for a minimum of 28 days (minimum of 3,500 psi compressive strength). The use of concrete curing agents, if any, shall be of a sodium silicate base only; others require written approval from NEOGARD®.
 3. That damaged areas of the concrete substrate be restored to match adjacent areas. Use 70714/70715-09 epoxy and oven-dry silica aggregate approved by NEOGARD® for filling and leveling at a ratio of one part epoxy mixed with four parts aggregate by volume.

3.2 PREPARATION

- A. Protection:
 1. Protect adjacent surfaces from damage resulting from work of this trade. If necessary, mask and/or cover adjacent surfaces, fixtures, equipment, etc. by suitable means.

2. Provide a suitable work station to mix the coating materials.

B. Surface Preparation:

1. Cleaning: Surfaces contaminated with oil or grease shall be vigorously scrubbed with a power broom and a strong, non-sudsing detergent. Thoroughly wash, clean and dry. Areas where oil or other contaminants penetrate deep into the concrete may require removal by mechanical methods.
2. Steel shotblast the surface to remove surface contaminants. Proper care and procedure should be taken to leave the concrete surface as unopened as possible. An improper steel shotblast can cause "pinholes" in concrete surfaces, which can result in blister problems during the application of the general use epoxy flooring system. Note: Shotblasting does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to insure proper bonding of the epoxy flooring.
3. Non-moving Cracks: After shotblasting, fill all non-moving cracks with 70714/70715-09 epoxy mixed with P1934 fumed silica to form a paste. The mix ratio is one part 70714/70715-09 epoxy to 2 (up to 3) parts P1934 fumed silica by volume.
4. Moving Cracks or Control Joints: Route all large cracks, remove dust and debris, and fill flush with 70718/70719 flexible epoxy.
5. Moving Control Joints: Seal secondary control joints with 70991 sealant. Re-incorporate expansion joints and control joints into flooring system if conditions require. Consult NEOGARD® for details on moving cracks, expansion joint details and moving control joints.
6. Surface Condition: Concrete must be free of hydrostatic, capillary or moisture vapor pressure. Substrates in contact with ground must have a properly installed, effective vapor barrier to help prevent potential problems resulting from hydrostatic, capillary or moisture vapor pressure. Moisture content of concrete not to exceed four pounds per 1,000 square feet per 24 hours when tested by the referee or quantitative calcium chloride test method.
7. Do not apply materials unless surface to receive coating is clean and dry.

3.3 APPLICATION

- A. Primer: Mix 70714/70715-09 clear epoxy at a ratio of 2:1 for three minutes. Apply at a rate of 200 square feet per gallon (8 mils DFT) to prepared substrate. Primer should be tack free before applying base coat.
- B. Base Coat: Mix 70714/70715-09 clear or pigmented epoxy at a ratio of 2:1 for three minutes. Apply at a minimum rate of 130 square feet per gallon (12 mils

DFT) to prepared substrate and allow to cure 8 to 12 hours @ 70°F (21.1°C) or until tack free.

- C. Topcoat: Mix 70714/70715-09 clear or pigmented epoxy at a ratio of 2:1 by volume. Apply at a minimum rate of 130 square feet per gallon (12 mils DFT) to prepared substrate and allow to cure 24 hours @ 70°F (21.1°C) before allowing foot traffic.
- D. Optional Neogrip Textured Finish: To achieve a limited slip-resistant surface, a third topcoat of 70714/70715-09 epoxy must be applied. Add 4 to 6 ounces by volume of Neogrip spheres to one gallon of 70714. Mix one gallon of 70714 with the Neogrip spheres to 1/2 gallon of 70715-09 and mix for three minutes. The coverage rate for the final topcoat must be applied at 350 to 400 square feet per gallon to yield an average nominal thickness of 4 mils WFT. Note: Installing the textured

finish thicker than 4 mils WFT will cause the Neogrip spheres to sink into the 70714/70715-09 epoxy coating, thus eliminating the desired slip-resistant texture.

3.4 CLEANING

- A. Remove debris resulting from completion of coating operation from the project site.
- B. Reference Seamless Flooring Systems Manual for typical cleaning methods.

3.5 PROTECTION

- A. After completion of application, do not allow heavy traffic on coated surfaces for a period of at least 24 hours at 75°F (23.8°C), or until completely cured 7 days @ 70°F (21.1°C).

END OF SECTION

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. WG-32GS CSI.indd

NEOGARD®

Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com